

POM X-Glide

This copolymer acetal grade, contains PE and PE-UHMW, this helps to improve the friction and dry sliding behavior. Squeaking noises are minimized. POM + PE engineered plastics are used as dynamically stressed building blocks such as bearing bushings or sliding plates for the food industry.

Physical Properties (indicative values)

GENERAL PROPERTIES	Test Method	Value
Density	ISO 1183 DIN 53479	1.35 g/cm ³
Water absorption in air 50% r.h.		0.20%
Absorption 23-C in water-saturation		0.80%
MECHANICAL PROPERTIES		
Tensile Strength at yield at break	ISO 527-2 DIN53455	43MPa
Elongation at break	ISO 527-2 DIN53455	15%
Tensile Modulus of elasticity	ISO 527 DIN53455	2200 MPa
Impact strength Charpy 7,5 J	ISO R179/1eU DIN53453	50 KJ/ mm ²
Notched impact strength Charpy	ISO179/3eA DIN53453	5 KJ/ mm ²
Ball indentation hardness	ISO2039.1 DIN53456	110MPa
Rockwell hardness (dry)	ISO2039.2	
Coefficient of friction to steel ^[12]		0.19
THERMAL PROPERTIES		
Melting point		166°C
Thermal conductivity	DIN 52612	--W/(km)
Deformation at temperature HDT ^[15]	ISO 75 DIN 53461	115°C
Linear expansion coefficient 23-60°C	ISO11359	140 x 10 ⁻⁶ K ⁻¹
Operating temperature continuously ^[17]		100°C
Operating temperature short period-no load ^[18]		140°C
TECHNOLOGICAL SOLUTIONS		
Minimum operating temperature ^[19]		-30°C
Flammability UL 94 (3-6 mm thickness)	UL94	HB
ELECTRICAL PROPERTIES		
Dielectric constant at 1MHz	ISO 250 DIN53483	3.8
Dielectric strength	ISO 243 DIN 53481	35 KV/mm
Volume resistivity	ISO 93 DIN 53482	10 ⁻¹⁵ Ωcm

- Figures relate to specimen conditioned at 23°C and 50% RH. Figures between brackets relate to dry specimen. Figures for materials marked with * can change according to their moisture content.

- Figures refer to un-coloured specimen either injection moulded or machined in the easiest way. Tests made on specimen of different sizes give slightly different results.

- [12] Test on ground steel dry specimen load =0,05 N/mm² speed=0,6 m/s.

- [15] Deformation at temperature. HDT at 1,8 N/mm²

- [17] Operating temperature continuously 5000h From 23°C upwards the materials' features change in a non-uniform and disproportional way due to the heat. The quoted limits are indicative and based on a tensile stress of 50% of the value at 23° C.

- [18] Operating temperature short period (no load)

- [19] The mechanical features decrease with a reduction in temperature and are influenced also by other factors (moisture, etc.). The quoted value does not take into consideration impact conditions or heavy loads.

- A Amorphous

- All values and information provided are based on information currently in our possession and/or results archived from tests conducted in our laboratories. They are given in good faith and are not legally binding. For any particular application, the technical staff of Omnia Plastica spa is at your disposal to assist with solving your problem.

This product data sheet and any data or specifications presented on our website shall provide promotional and general information about Plastim Limited Products and shall serve as a preliminary guide. All data and descriptions relating to our products are of an indicative nature only. Neither this data sheet nor any data and specifications presented on our website shall create or be implied to create any legal or contractual obligation.

It solely remains the customers responsibility to test and assess the suitability and compatibility of Plastim's Products for it's intended applications, processes and uses. The customer undertakes all liability in respect of the applictaion, processing or use of the aforementioned information or product .