

OmniPEEK

Poly-ether-ether-ketone (unfilled)

OmniPEEK is an advanced high performance semi-crystalline thermoplastic. Combining high mechanical strength and dimensional stability with excellent temperature and harsh chemical resistances.

Properties	Test method	Unit	Value
Mechanical			
Tensile strength	ISO 527	MPa	≥105
Elongation at break	ISO 527	%	≥ 15
Modulus of elasticity (tensile)	ISO 527	GPa	≥ 4.0
Modulus of elasticity (flexural)	ISO 178	MPa	≥ 4.0
Notch impact strength	ISO 179	KJ / m ²	≥ 5.6
Flexural strength	ISO 178	MPa	≥ 160
Compressive stress 5 % strain	ISO 604	MPa	-
Compressive modulus	ISO 604	MPa	-
Shore hardness	ISO 868	D	-
Rockwell hardness	ISO 2039-2	HRM	≥ 150
Ball indentation hardness	ISO 2039	MPa	-
Thermal			
Melting temperature	ISO 3146	°C	-
Glass transition temperature (Tg)	ISO 11357	°C	-
Thermal conductivity	ISO 8302	W / (m * K)	≤ 0.5
Coef. of linear thermal expansion	ISO 11359-2	10 ⁻⁴ / K	≤ 65
Long term service temperature	UL 746B *	°C	240
Short term service temperature	See note *	°C	-
Heat deflection temperature	ISO 75-2	°C	≥150
Flammability	UL 94	-	V-O
Flammability (oxygen index)	ISO 4589	%	
Electrical			
Dielectric constant at 1MHz	IEC 60243-1	l	3.66
Dissipation factor at 1MHz	IEC 60250	-	-
Volume resistivity	IEC 62631-3-1	Ω * cm	≥ 10 ¹⁴⁻¹⁶
Surface resistivity	IEC 60093	Ω	-
Dielectric strength	IEC 60243-1	kV / mm	≥ 15
Tracking resistance (CTI)	IEC 60112	V	-
Additional Data			
Density	ISO 1183-1	g / cm ³	1.3
Water absorption 24h (saturation)	ISO 62	%	≤ 0.05
Humidity absorption (saturation)	ISO 62	%	-
Food compliance	EEC	-	-
Food compliance	FDA	-	-
Coefficient of Friction (pin-on-disk)	ISO 7148-2	-	-
Shapes	Rod (8 - 200mm Ø)	Sheet (5 -100mm Thk)	Tube (on request)
Colour	Natural		

- PEEK retain flexural and tensile properties at high temperatures.

The conditioned material values stated are average test results. The data provides information about our products and offers a guide for material selection. This does not provide an assurance of specific properties or the products suitability for a particular application.

It solely remains the customers responsibility to test and assess the suitability and compatibility of Plastim's products for it's intended applications, processes and uses. The customer undertakes all liability in respect of the application, processing or use of the aforementioned information or product.

- * Long term service temperature are based on the thermal ageing of the polymer by oxidation, resulting in a decrease in mechanical capabilities
- * Short term service temperature only applies to very low mechanical stress for a very limited time only.

Properties can vary depending on the raw shape selected and the degree of crystallisation. The actual property values of a finished product may differ from the indicated values stated.