

**OmniPEI Ultem®**

Polyphenylene ether (unfilled)

OmniPEI is an unreinforced amorphous high-performance thermoplastic, offering high mechanical, thermal and electrical properties. Including very high rigidity and exceptional creep resistance over a wide operating temperature range.

Properties	Test method	Unit	Value
<b>Mechanical</b>			
Tensile strength	ISO 527	MPa	≥110
Elongation at break	ISO 527	%	≥10
Modulus of elasticity (tensile)	ISO 527	GPa	≥3.1
Modulus of elasticity (flexural)	ISO 178	GPa	≥3.1
Notch impact strength	ISO 179	KJ / m <sup>2</sup>	≥4
Flexural strength	ISO 178	MPa	≥150
Compressive stress 5 % strain	ISO 604	MPa	-
Compressive modulus	ISO 604	MPa	-
Shore hardness	ISO 868	D	-
Rockwell hardness	ISO 2039-2	HRM	≥110
Ball indentation hardness	ISO 2039	MPa	-
<b>Thermal</b>			
Melting temperature	ISO 3146	°C	-
Glass transition temperature (Tg)	ISO 11357	°C	215
Thermal conductivity	ISO 22007	W / (m * K)	-
Coef. of linear thermal expansion	ISO 11359-2	10 <sup>-6</sup> / K	≤60
Long term service temperature	UL 746B	°C	170
Short term service temperature	See note *	°C	-
Heat deflection temperature	ISO 75-2	°C	200
Flammability	UL 94	-	V0
Flammability (oxygen index)	ISO 4589	%	-
<b>Electrical</b>			
Dielectric constant at 1MHz	IEC 62631-2-1	Ω * cm	3.4
Dissipation factor at 1MHz	IEC 60250	10 <sup>6</sup> Hz	-
Volume resistivity	IEC 62631-3-1	Ω * cm	≥ 10 <sup>15-17</sup>
Surface resistivity	IEC 60093	Ω	-
Dielectric strength	IEC 60243-1	kV / mm	≥26
Tracking resistance (CTI)	IEC 60112	V	-
<b>Additional Data</b>			
Density	ISO 1183-1	g / cm <sup>3</sup>	1.28
Water absorption 24h (saturation)	ISO 62	%	≤ 0.4
Humidity absorption (saturation)	ISO 62	%	-
Food compliance	EEC	-	-
Food compliance	FDA	-	-
Coefficient of Friction (pin-on-disk)	ISO 7148-2	-	-
Shapes	Rod (8 → 150 Ø)	Sheet (6 → 100mm thk)	-
Colour	Translucent Amber		

- OmniPEI Ultem® offers chemical and hydrolysis resistance to withstand repeated autoclaving cycles.

The conditioned material values stated are average test results. The data provides information about our products and offers a guide for material selection. This does not provide an assurance of specific properties or the products suitability for a particular application.

It solely remains the customers responsibility to test and assess the suitability and compatibility of Plastim's products for its intended applications, processes and uses. The customer undertakes all liability in respect of the application, processing or use of the aforementioned information or product.

- \* Long term service temperature are based on the thermal ageing of the polymer by oxidation, resulting in a decrease in mechanical capabilities
- \* Short term service temperature only applies to very low mechanical stress for a very limited time only.

Properties can vary depending on the raw shape selected and the degree of crystallisation. The actual property values of a finished product may differ from the indicated values stated.